

09/824,671
NGB.055

2

at least one air vent in said case; and
an air-permeable filter provided in said at least one air vent, said air-permeable filter comprising:

B2
cont. a laminate comprising:

at least one porous material layer comprising at least one resin selected from the group consisting of fluororesin and polyolefin resin; and

at least one air-permeable substrate layer having a tensile strength of 1 MPa or more, and having an outer surface bonded to said at least one porous material layer, wherein a Gurley number of said air-permeable filter is less than 100 sec/100 ml.

B3
8. (Twice Amended) The air-permeable filter for an ink cartridge according to claim 2, wherein the Gurley number of the air-permeable filter is from 0.1 sec/100 ml to less than 100 sec/100 ml.

9. (Twice Amended) The air-permeable filter for an ink cartridge according to claim 8, wherein the Gurley number of the air-permeable filter is from 0.5 sec/100 ml to less than 100 sec/100 ml.

B4
17. (Amended) An air-permeable filter comprising:
at least one porous material layer comprising at least one of fluororesin and polyolefin resin; and
at least one air-permeable substrate layer having a tensile strength of 1 MPa or more, and having an outer surface bonded to said at least one porous material layer, wherein a Gurley number of said air-permeable filter is less than 100 sec/100 ml.

B5
19. (Amended) The air-permeable filter according to claim 17, wherein a Gurley number of the air-permeable filter is from 0.5 sec/100ml to less than 100 sec/100 ml.

FAX RECEIVED
JAN 13 2003
GROUP 1700